



HAL
open science

Controlling the propagation of light and sound in silicon waveguides by means of subwavelength nanostructuring

J. Zhang, D. Oser, T. T. D. Dinh, X. Le Roux, M. Montesinos, C. Lafforgue, F. Mazeas, D. Pérez-Galacho, D. Benedikovic, E. Durán-Valdeiglesias, et al.

► **To cite this version:**

J. Zhang, D. Oser, T. T. D. Dinh, X. Le Roux, M. Montesinos, et al.. Controlling the propagation of light and sound in silicon waveguides by means of subwavelength nanostructuring. META 2020, the 11th International Conference on Metamaterials, Photonic Crystals and Plasmonics, Jul 2020, Warsaw (POLAND), Poland. hal-04490397

HAL Id: hal-04490397

<https://universite-paris-saclay.hal.science/hal-04490397v1>

Submitted on 5 Mar 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Controlling the propagation of light and sound in silicon waveguides by means of subwavelength nanostructuring

J. Zhang¹, D. Oser¹, T. T. D. Dinh¹, X. Le Roux¹, M. Montesinos¹, C. Lafforgue^{1,2}, F. Mazeas³, D. Pérez-Galacho⁴, D. Benedikovic¹, E. Durán-Valdeiglesias¹, V. Vakarin¹, O. Ortiz¹, O. Alibart³, P. Cheben^{5,6}, S. Tanzilli³, L. Labonté³, D. Marris-Morini¹, E. Cassan¹, D. Lanzillotti-Kimura¹, L. Vivien¹, and C. Alonso-Ramos¹

¹Université Paris-Saclay, CNRS, Centre de Nanosciences et de Nanotechnologies, 91120, Palaiseau, France

²École Normale Supérieure Paris-Saclay, Université Paris-Saclay, 94230 Cachan, France

³Université Côte d'Azur, CNRS, Institut de Physique de Nice, Parc Valrose, 06108 Nice Cedex 2, France

⁴ITEAM research institute, Universitat Politècnica de València, Camino de Vera s/n, 46022, Valencia, Spain

⁵National Research Council, Ottawa, K1A 0R6, Canada

⁶Center for Research in Photonics, University of Ottawa, Ottawa K1N6N5, Canada

*corresponding author, E-mail: carlos.ramos@c2n.upsaclay.fr

Abstract

Periodically patterning silicon with a pitch sufficiently small to suppress diffraction effects opens new degrees of freedom to control light propagation in silicon photonic circuits with unprecedented flexibility. Concurrently, near-infrared photons and GHz phonons in nanoscale Si waveguides have comparable wavelengths. Thus, subwavelength nanostructuring has a great potential to shape light-sound interactions in silicon waveguides. Here, we present our most recent results on the subwavelength engineering of silicon for the implementation of high-performance photonic and optomechanical components.

1. Introduction

Periodically patterning silicon with a pitch sufficiently small to suppress diffraction effects opens new degrees of freedom to control light propagation in silicon photonic circuits with unprecedented flexibility [1-3]. Indeed, this subwavelength metamaterial concept has enabled the demonstration of several Si photonic components, some with the best performance ever reported [2,3]. On the other hand, near-infrared photons and GHz phonons in nanoscale Si waveguides have comparable wavelengths (around 1 μm) [4,5]. Thus, subwavelength nanostructuring of silicon has a great potential to shape the properties (confinement, dispersion, etc.) of both, photonic and phononic modes, thereby opening new routes to engineer light-sound interactions in silicon, e.g. Brillouin scattering. Here, we present our most recent results on the subwavelength engineering of silicon for the implementation of high-performance photonic and optomechanical components.

2. Spectral filters

Bragg optical filters are widely used in photonics for advanced on-chip signal manipulation. However, achieving narrowband Bragg filters with large rejection levels is often hindered by fabrication constraints and imperfections. We have developed a new generation of high-performance Bragg filters that exploit subwavelength grating (SWG) and symmetry engineering to overcome this bandwidth-rejection trade-off. We experimentally show flexible control over the width and depth of the Bragg resonance [6]. We have also developed a novel approach that leverages non-coherent cascading of multi-modal waveguide Bragg gratings to achieve ultra-high rejection levels, exceeding 80 dB [7]. The proposed architecture comprises several filter sections implemented with Bragg gratings that couple back-reflections into a high-order waveguide mode. These sections are connected by single-mode waveguides that radiate back-reflections propagating in a high-order mode. This configuration avoids any coherent interaction among filters, enabling efficient cascading even in the presence of phase errors. These results pave the way for the implementation of high-performance on-chip pump-rejection filters with a great potential for Si-based quantum photonic circuits.

3. Optomechanical silicon waveguides exploiting subwavelength engineering

Brillouin scattering is a third order optical nonlinear process that results from light-sound coupling that has been widely exploited fiber optics. The availability of materials co-confining phonons and photons in the same photonic device is fueling the study of Brillouin interaction on chip [10,11]. Recent demonstrations have shown Brillouin interactions in

silicon chips with strengths that surpassed those of Kerr and Raman effects [4,5]. Acoustic phonons with GHz frequencies and near infrared photons in nanometric-scale silicon waveguides have very similar wavelengths, enabling high-efficiency coupling that resulted in the demonstration of remarkably large Brillouin gain [4] and even Brillouin lasing [5]. Silicon membranes are an appealing solution to efficiently confine photons and phonons [5,12]. Still, efficient Brillouin interactions in Si membranes are hampered by acoustic leakage, due to coupling to the lateral silicon slabs. This loss has been alleviated by inserting air gaps [5] or by implementing phononic stop bands in the transversal dimension [12]. However, the efficiency of these approaches is limited by weak photon-phonon overlap or narrowband operation. Here, we present a new waveguide geometry that harnesses geometrical subwavelength softening to minimize the loss of acoustic modes and subwavelength index engineering to confine optical modes. The proposed subwavelength-lattice waveguide, that works well below the photonic and phononic bandgaps, provides simultaneous enhancement of the quality factor of the acoustic mode and the photon-phonon interaction. Our calculations predict a remarkably large Brillouin gain exceeding $10000 \text{ (W}\cdot\text{m)}^{-1}$. These results open exciting prospects to achieve up to a three-fold improvement in Brillouin gain, compared to previous demonstrations [4,5,13].

4. Conclusions

In conclusion, we exploit the subwavelength nanostructuring of Si photonic waveguides to demonstrate a new generation of high-performance Bragg grating filters. In addition, we present a new approach to optimize Brillouin scattering in silicon optomechanic waveguides, based on subwavelength engineering of light and sound. The proposed optomechanic waveguide relies upon a silicon membrane with a subwavelength-lattice structuration to optimize the photon-phonon interaction and the acoustic quality factor, simultaneously. Our calculations predict that the proposed waveguide may provide high acoustic quality factor up to 2000 and Brillouin gain up to $10000 \text{ (W}\cdot\text{m)}^{-1}$. We believe these results open a new route to engineer photon-phonon interactions exploiting subwavelength-lattice structuration in silicon opto-mechanic waveguides.

Acknowledgements

This work was funded by the Agence Nationale de la Recherche (MIRSPEC ANR-17-CE09-0041, BRIGHT ANR-18-CE24-0023-01, SITQOM DS0710) and the French Industry Ministry (Nano2022 project under IPCEI program).

References

[1] P. J. Bock, P. Cheben, J. H. Schmid, J. Lapointe, A. Delâge, S. Janz, G. C. Aers, D.-X. Xu, A. Densmore, T. J. Hall, Subwavelength grating periodic structures in silicon-on-insulator: a new type of microphotonic waveguide, *Opt. Express* 18: 20251-20262, 2010.

- [2] R. Halir, P. Bock, P. Cheben, A. Ortega-Moñux, C. Alonso-Ramos, J. H. Schmid, J. Lapointe, D.-X. Xu, J. G. Wangüemert-Pérez, I. Molina-Fernández, S. Janz, Waveguide sub-wavelength structures: a review of principles and applications, *Laser Photonics Rev.* 8: 25-49, 2015.
- [3] P. Cheben, R. Halir, J. H. Schmid, H. A. Atwater, D. R. Smith, Subwavelength integrated photonics, *Nature* 560: 565-572, 2018.
- [4] R. Van Laer, B. Kuyken, D. Van Thourhout, R. Baets, Interaction between light and highly confined hypersound in a silicon photonic nanowire, *Nat. Photon.* 9: 199-203, 2015.
- [5] T. Otterstrom, R. O. Behunin, E. A. Kittlaus, Z. Wang, P. T. Rakich, A silicon Brillouin laser, *Science* 360: 1113-1116, 2016.
- [6] D. Oser, D. Pérez-Galacho, C. Alonso-Ramos, X. Le Roux, S. Tanzilli, L. Vivien, L. Labonté, E. Cassan, Subwavelength engineering and asymmetry: two efficient tools for sub-nanometer-bandwidth silicon Bragg filters, *Opt. Lett.* 43: 3208-3211, 2018.
- [7] D. Oser, F. Mazeas, X. Le Roux, D. Pérez-Galacho, O. Alibart, S. Tanzilli, L. Labonté, D. Marris-Morini, L. Vivien, E. Cassan, C. Alonso-Ramos, Coherency-broken Bragg filters: overcoming on-chip rejection limitations, *Laser Photonics Rev.* 13: 1800226, 2019.
- [8] M. Esmann, F. R. Lamberti, A. Harouri, L. Lanco, I. Sagnes, I. Favero, G. Aubin, C. Gomez-Carbonell, A. Lemaître, O. Krebs, P. Senellart, N. D. Lanzillotti-Kimura, Brillouin scattering in hybrid optophononic Bragg micropillar resonators at 300 GHz, *Optica* 6: 854-859, 2019.
- [9] G. Arregui, N. D. Lanzillotti-Kimura, C. M. Sotomayor-Torres, P. D. García, Anderson photon-phonon colocalization in certain random superlattices, *Phys. Rev. Lett.* 122: 043903, 2019.
- [10] F. R. Lamberti, Q. Yao, L. Lanco, D. T. Nguyen, M. Esmann, A. Fainstein, P. Sesin, S. Anguiano, V. Villafaña, A. Bruchhausen, P. Senellart, I. Favero, N. D. Lanzillotti-Kimura, Optomechanical properties of GaAs/AlAs micropillar resonators operating in the 18 GHz range, *Opt. Express* 25: 24437-24447, 2017.
- [11] M. K. Schmidt, C. G. Poulton, G. Z. Mashanovich, G. T. Reed, B. J. Eggleton, M. J. Steel, Suspended mid-infrared waveguides for stimulated Brillouin scattering, *Opt. Express* 27: 4976-4989, 2019.
- [12] E. A. Kittlaus, H. Shin, P. T. Rakich, Large Brillouin amplification in silicon, *Nat. Photon.* 10: 463-468, 2015.